

Fermi-Liquid Interactions in d -Wave Superconductors

M. B. Walker

Department of Physics, University of Toronto, Toronto, Ont. M5S 1A7
(February 1, 2008)

This article develops a quantitative quasiparticle model of the low-temperature properties of d -wave superconductors which incorporates both Fermi-liquid effects and band-structure effects. The Fermi-liquid interaction effects are found to be classifiable into strong and negligible renormalization effects, for symmetric and antisymmetric combinations of the energies of $k \uparrow$ and $-k \downarrow$ quasiparticles, respectively. A particularly important conclusion is that the leading clean-limit temperature-dependent correction to the superfluid density is not renormalized by Fermi-liquid interactions, but is subject to a Fermi velocity (or mass) renormalization effect. This leads to difficulties in accounting for the penetration depth measurements with physically acceptable parameters, and hence reopens the question of the quantitative validity of the quasiparticle picture.

PACS numbers: 74.20.-z, 74.25.Jb, 74.50.+r, 74.80.fp

There is now considerable experimental evidence that the cuprate high T_c superconductors exhibit the simple power law temperature dependences predicted by the quasiparticle picture for their thermodynamic and transport properties at temperatures well below T_c . For example, penetration depth measurements find that the superfluid density exhibits a low-temperature clean-limit linear in T temperature dependence¹, in agreement with theory². The NMR relaxation rate exhibits the expected T^3 temperature dependence³. The predicted effect of impurities in giving rise to a universal thermal conductivity^{4,5} has been confirmed⁶. The clean limit specific heat varying as T^2 appears to have been observed^{7,8}. Even the electrical transport relaxation rate observed in microwave conductivity experiments⁹, which had resisted explanation for some time, has now been explained in terms of a quasiparticle picture¹⁰.

Whether or not the magnitudes of the coefficients of the above power law temperature dependences are accurately given by a quasiparticle description is at present an open question. A recent study correlating these different coefficients¹¹ concludes that the quasiparticle model may be successful here also provided a Fermi-liquid interaction factor multiplying the superfluid density is treated as an adjustable parameter. The contention of this article is that there is however no Fermi-liquid interaction renormalization of the linear in T contribution to the inverse square penetration depth. There is instead a renormalization by a factor involving the ratio of a band Fermi velocity to a Landau quasiparticle Fermi velocity. The difficulty now is that a physically unreasonable value of this renormalization parameter is obtained from experiment. This reopens the question of to what extent the quasiparticle picture can provide an accurate quantitative picture of the low temperature behavior of the high T_c superconductors. Recent debate on correctness of the quasiparticle picture is also occurring in connection with ARPES experiments^{12,13}, and in connection with the role of phase fluctuations of the complex order parameter in

the determination of the temperature dependence of the superfluid density¹⁴.

The potential importance of Fermi-liquid interactions in renormalizing the superfluid density has been emphasized in Refs. 15 and 16. These papers note that Fermi-liquid renormalization effects in d -wave superconductors can be either strong or weak according as the contributing quasiparticles are from the entire Fermi surface, or confined to the nodal points where the d -wave gap goes to zero. Both expect a strong renormalization effect for the superfluid density, whereas this article does not find such an effect.

This article shows that the physics of Fermi liquid effects in d -wave superconductors has an interesting symmetry property. This manifests itself when the quasiparticle energies are separated into parts that are Symmetric and Antisymmetric combinations of the energies of the $+k \uparrow$ and $-k \downarrow$ states. (The calligraphic letters $\mathcal{S}$ and $\mathcal{A}$ are used here to emphasize the difference with the more usual definition of the symmetric and antisymmetric combinations with respect to $+k \uparrow$ and $+k \downarrow$ states common in normal state analyses, e.g. see Eq. 1.32 of Ref. 17.) In the presence of Fermi-liquid interactions, the Symmetric and Antisymmetric corrections to the quasiparticle energies obey integral equations that are independent of each other, and they are renormalized differently. The Symmetric energy corrections exhibit strong Fermi-liquid renormalization effects, while the Antisymmetric energy corrections exhibit relatively weak temperature-dependent renormalizations that can often be neglected.

Temperature gives a Symmetric correction to the quasiparticle energy because $+k \uparrow$ and $-k \downarrow$ states are affected in the same way by temperature. A superfluid flow generates an Antisymmetric correction since the components of $+k$ and $-k$ along the superfluid velocity have opposite signs. Also the Zeeman interaction generates an Antisymmetric correction because the spin $\uparrow$ and spin $\downarrow$ contributions to the energy have opposite

signs. Thus the superfluid density and the magnetic susceptibility are negligibly renormalized by Fermi-liquid interactions, while the effects of temperature (although relatively small) are strongly renormalized by Fermi-liquid interactions.

The approach of this article to the inclusion of Fermi-liquid interactions in the study of the superconducting state follows the intuitively appealing approach of Ref. 18, which is consistent with more formal correlation function approaches.^{19,20} Rather than starting with a band energy in the absence of electron-electron interactions of $\epsilon_k^b = \hbar^2 k^2 / (2m)$ as in Ref. 18, however, this article allows ϵ_k^b to be an arbitrary function of $\mathbf{k}$ so as to be able to account for anisotropic Fermi surface effects. To form a Hamiltonian from ϵ_k^b the substitution $\hbar\mathbf{k} \rightarrow -i\hbar\nabla - e\mathbf{A}/c$ is made. Also, this article studies only equilibrium properties, and does not develop a kinetic equation. Other studies of Fermi liquid interactions in unconventional superconductivity include Refs. 21,22.

The Hamiltonian describing the excitations of the superconducting state has the following form:

$$\mathcal{H} = \sum_k [c_{k\uparrow}^\dagger \ c_{-k\downarrow}] \begin{bmatrix} \zeta_k + \lambda_k & \Delta_k \\ \Delta_k & -\zeta_k + \lambda_k \end{bmatrix} \begin{bmatrix} c_{k\uparrow} \\ c_{-k\downarrow}^\dagger \end{bmatrix}. \quad (1)$$

Here $\zeta_k = \xi_k + \delta\varepsilon_k^S + h_k^S$ where ξ_k is the Landau quasiparticle energy relative to the chemical potential (neglecting quasiparticle interactions), $\lambda_k = \delta\varepsilon_k^A + h_k^A$, and Δ_k is the momentum-dependent gap function appropriate for d -wave symmetry. Fermi liquid interactions give a contribution to the energy of a quasiparticle with momentum $\mathbf{k}$ and spin σ due to other excited quasiparticles which is^{18,17}.

$$\delta\varepsilon_{k\sigma} = \frac{1}{L^2} \sum_{k'} [f_{kk'}^{\sigma\sigma} \delta n_{k'\sigma} + f_{kk'}^{\sigma\bar{\sigma}} \delta n_{k'\bar{\sigma}}]. \quad (2)$$

where $\bar{\sigma} \equiv -\sigma$, $n_{k\sigma} = \langle c_{k\sigma}^\dagger c_{k\sigma} \rangle$, and δ indicates a variation due to the excitation of other electrons and holes, either by temperature or by the presence of external fields. (The factor L^{-2} occurs in Eq. 2 because the intention is to develop a model applicable to superconductivity in a two-dimensional copper-oxide plane of a high T_c superconductor having area L^2 .) An important step in the analysis, as described qualitatively above, is the separation of the Fermi liquid interactions into Symmetric and Antisymmetric parts defined by

$$\delta\varepsilon_k^A = \frac{1}{2} [\delta\varepsilon_{k\uparrow} - \delta\varepsilon_{-k\downarrow}], \quad \delta\varepsilon_k^S = \frac{1}{2} [\delta\varepsilon_{k\uparrow} + \delta\varepsilon_{-k\downarrow}]. \quad (3)$$

The quantities h_k^A and h_k^S in $\mathcal{H}$ represent generalized external fields. For example, in the case of an external magnetic field acting on the orbital motion of the electrons, the gap function will acquire a complex phase. This phase factor can be removed by a gauge transformation, $c_{k\sigma} \rightarrow c_{k\sigma} \exp(i\theta)$, the end result of which is

the addition of the field $h_k^A = \mathbf{v}_k^b \cdot \mathbf{p}_s$, $h_k^S = 0$, where $\mathbf{v}_k^b \equiv \partial\epsilon_k^b / \partial\mathbf{k}$, to the Hamiltonian. Here $\mathbf{p}_s = \hbar\nabla\theta - e\mathbf{A}/c$ is the superfluid momentum, which is assumed to be sufficiently slowly varying spatially that its gradients can be neglected. The velocity $\mathbf{v}_k^b$ that appears in h_k^A is the bare band velocity, unrenormalized by the electron-electron interaction, as noted following Eq. 12 of Ref. 18, and it is this same velocity that appears in the expression for the quasiparticle contribution to the current density (Eq. 5 below). On the other hand, the electron-electron interaction contributes to the quasiparticle energy ξ_k defined in and following Eq. 1, and hence affects the quasiparticle velocity v_F that occurs in $E_k^{(0)}$ below. The differences in these two velocities have important quantitative consequences for the interpretation of the penetration depth data, as will be seen below.

The Hamiltonian of Eq. 1 can be used to find the thermal equilibrium expectation value of the electrical current density operator giving, for the electrical current density $\mathbf{J} = \eta_g \mathbf{p}_s + \mathbf{J}_{qp}$, with the gauge contribution determined by

$$\eta_g = \frac{e}{2L^2} \sum_{k\sigma} n_{k\sigma} \frac{1}{\hbar^2} \left(\frac{\partial^2}{\partial k_x^2} + \frac{\partial^2}{\partial k_y^2} \right) \epsilon_k^b, \quad (4)$$

and the quasiparticle contribution given by

$$\mathbf{J}_{qp} = \frac{e}{L^2} \sum_{k\sigma} \mathbf{v}_k^b f(E_{k,\sigma}), \quad (5)$$

$f(E_{k,\sigma})$ is the Fermi-Dirac distribution function, and the $E_{k,\sigma}$ are the Bogoliubov quasiparticle energies defined below. The case of an external magnetic field H acting on the spin degrees of freedom is described by taking $h_k^A = \mu_B H$, $h_k^S = 0$. In both of these cases, the magnetic field acts only on the Antisymmetric mode, and has no effect on the Symmetric mode of excitation.

In addition to causing changes in the energy of a quasiparticle (as in Eq. 2), excited quasiparticles can give rise to changes in the gap function¹⁸. There are however no changes that are linear in the superfluid momentum²², and this effect will therefore be neglected.

The diagonalization of the Hamiltonian of Eq. 1 gives

$$\mathcal{H} = \sum_{k\sigma} E_{k,\sigma} \gamma_{k,\sigma}^\dagger \gamma_{k,\sigma}, \quad E_{k,\sigma} = E_{\sigma k} + \sigma(\delta\varepsilon_{\sigma k}^A + h_{\sigma k}^A) \quad (6)$$

where $\sigma = \pm 1$, $E_k = \sqrt{\zeta_k^2 + \Delta_k^2}$, and the $\gamma_{k,\sigma}^\dagger$ are operators creating Bogoliubov quasiparticles.

Later, the energy $E_k^{(0)} = \sqrt{\xi_k^2 + \Delta_k^2}$ describing the quasiparticle spectrum in the absence of other excited quasiparticles is also used. For a d -wave superconductor, the quasiparticle energy can be parameterized⁴ in the neighborhood of the Fermi-surface nodal points (see Fig. 1) as $E_k^{(0)} = \sqrt{(p_1 v_F)^2 + (p_2 v_2)^2}$, where p_1 and p_2 are components of the momentum relative to the nodal point in directions perpendicular and parallel to the Fermi line.

At low temperatures, only quasiparticles close to these four points can be thermally excited.

Using Eq. 2 in Eq. 3, keeping only terms up to linear order in the $\delta\varepsilon$'s and h 's, and dropping some terms of order $k_B T/(\hbar k_F v_2)$ relative to those kept, yields the integral equations

$$\delta\varepsilon_k^S = \frac{1}{L^2} \sum_{k'} f_{kk'}^{(+)} \left[\frac{\xi_{k'}}{E_{k'}^{(0)}} f(E_{k'}^{(0)}) - \frac{\Delta_{k'}^2}{E_{k'}^{(0)3}} (\delta\varepsilon_{k'}^S + h_{k'}^S) \right] \quad (7)$$

and

$$\delta\varepsilon_k^A = \frac{1}{L^2} \sum_{k'} f_{kk'}^{(-)} \frac{\partial f}{\partial E_{k'}^{(0)}} (\delta\varepsilon_{k'}^A + h_{k'}^A), \quad (8)$$

where $f_{kk'}^{(\pm)} = f_{kk'}^{\sigma\sigma} \pm f_{k,-k'}^{\sigma\bar{\sigma}}$.




FIG. 1. The labelling of the nodes on the Fermi surface of $\text{YBa}_2\text{Cu}_3\text{O}_{6+x}$

Consider first the Symmetrical corrections to the quasiparticle energies (Eq. 7), and assume that there are no Symmetrical external fields other than temperature, i.e. $h_k^S = 0$ (as is the case for the external magnetic fields of most interest in this article, which are purely Antisymmetrical). Then the only term driving a nonzero contribution to $\delta\varepsilon_k^S$ is the term on the right hand side proportional to $f(E_{k'}^{(0)})$ and describing the effect of temperature. This term is proportional to T^3 , thus giving a $\delta\varepsilon_k^S \propto T^3$, and will not be important in contributing to the properties of interest at the temperatures satisfying $k_B T \ll \Delta_0$ (Δ_0 is the maximum gap). Thus $\delta\varepsilon_k^S$ will be neglected in calculations below.

Now from Eq. 8, which determines the Antisymmetrical corrections to the quasiparticle energies, it is clear that only the values of $\delta\varepsilon_k^A$ and h_k^A at the Fermi surface nodes are relevant to the low energy properties. Also, the solutions of Eq. 8 can be classified according to the irreducible representation of the point group C_{4v} (or 4mm) describing a tetragonal copper-oxide plane of a high T_c superconductor, the independent solutions being

$$\begin{aligned} \delta\varepsilon_{A_g}^A &= (\delta\varepsilon_1^A + \delta\varepsilon_2^A + \delta\varepsilon_3^A + \delta\varepsilon_4^A) / 4 \\ \delta\varepsilon_{xy}^A &= (\delta\varepsilon_1^A + \delta\varepsilon_2^A - \delta\varepsilon_3^A - \delta\varepsilon_4^A) / 4 \\ \delta\varepsilon_{Ex}^A &= (\delta\varepsilon_1^A + \delta\varepsilon_2^A + \delta\varepsilon_3^A + \delta\varepsilon_4^A) / 4 \\ \delta\varepsilon_{Ey}^A &= (\delta\varepsilon_1^A + \delta\varepsilon_2^A + \delta\varepsilon_3^A + \delta\varepsilon_4^A) / 4 \end{aligned} \quad (9)$$

where the indices 1,2,3 and 4 refer to the four nodes in the excitation spectrum, as defined in Fig. 1. The external fields h_k^A at the nodes can be similarly classified.

The solution of Eq. 8 now yields

$$\delta\varepsilon_\Gamma^A(T) = -h_\Gamma^A F_\Gamma^A(T) / [1 + F_\Gamma^A(T)] \quad (10)$$

with $F_\Gamma^A(T) = f_\Gamma^A \ln(2) k_B T / (2\pi \hbar^2 v_F v_2)$. Here Γ represents any of the irreducible representations present in Eqs. 9. The f_Γ^A 's are defined by

$$\begin{aligned} f_{A_g}^A &= f_{11}^a + f_{13}^a + 2f_{12}^a \\ f_{xy}^A &= f_{11}^a + f_{13}^a - 2f_{12}^a \\ f_E^A &= f_{11}^s - f_{13}^s \end{aligned} \quad (11)$$

where

$$f_{kk'}^{s,a} \equiv f_{kk'}^{\sigma\sigma} \pm f_{kk'}^{\sigma\bar{\sigma}} \quad (12)$$

are the symmetric and antisymmetric combinations of the Fermi-liquid parameters familiar from normal state analyses.¹⁷, and f_{12}^a for example is $f_{kk'}^a$ for k and k' at nodes 1 and 2, respectively.

It is also useful to use Eq. 7 to obtain an idea of how the Symmetrical external fields are renormalized by Fermi-liquid interactions. It is clear from Eq. 7 that a knowledge of the Fermi-liquid interaction on the entire Fermi surface is required and that $\delta\varepsilon_k^S$ must be determined on the entire Fermi surface. To obtain a rough idea of the nature of the solutions, consider a circular Fermi surface of radius k_F and look for a solution of A_g symmetry by considering a Fermi liquid interaction $f_{kk'}^{(+)} = f_{A_g}^S$, independent of k and k' , and a Symmetrical external field $h_{A_g}^S$ independent of k . The solution, which is also independent of k on the Fermi surface is

$$\delta\varepsilon_{A_g}^S = -\frac{F_{A_g}^S}{1 + F_{A_g}^S} h_{A_g}^S \quad (13)$$

where $F_{A_g}^S = f_{A_g}^S k_F / (\pi \hbar v_F)$. In contrast to the Antisymmetrical Fermi liquid parameters $F_\Gamma^A(T)$ obtained above, which go to zero linearly with temperature in the superconducting state in the clean limit (and hence have a dependence on temperature T explicitly indicated), the Symmetrical Fermi liquid parameter $F_{A_g}^S$ is temperature independent and of approximately the same magnitude as the corresponding normal state Fermi liquid parameter. The same can be seen to be true of the Symmetrical Fermi liquid parameters corresponding to other irreducible representations of C_{4v} . Note that the ratio of the Antisymmetrical to the Symmetrical Fermi-liquid F parameters is $F^A/F^S \approx (f^A/f^S)[k_B T/(\hbar k_F v_2)]$.

As noted above, the presence of a superfluid momentum contributes an Antisymmetrical external field to the Hamiltonian of Eq. 1. This external field corresponds to the E irreducible representation of C_{4v} with the p_{sx} and

p_{sy} components of $\mathbf{p}_s$ corresponding to the components Ex and Ey of Eq. 9. The current density is thus easily evaluated using Eq. 5 with Eqs. 6, 10 and 11. The result is $\mathbf{J}_{qp} = \eta_{qp}\mathbf{p}_s$ where

$$\eta_{qp}(T) = -\frac{2\ln 2e(v_F^b)^2 k_B T}{[1 + F_E^A(T)]\pi\hbar^2 v_F v_2} \quad (14)$$

Note that the Fermi liquid correction does not alter the clean limit linear in T contribution to the $\eta_{qp}(T)$, but rather makes a T^2 contribution (using $(1 + F)^{-1} \approx (1 - F + \dots)$). Thus there are no Fermi liquid corrections to the experimentally measured linear in T contribution to inverse square penetration depth. The penetration depth λ is thus given by

$$\lambda^{-2}(T) = \lambda^{-2}(0) - \frac{8\ln 2e^2}{c^2\hbar^2}\alpha^2 \frac{v_F}{v_2} k_B T + \dots \quad (15)$$

where $\alpha = (v_F^b/v_F)$, and $\lambda^{-2}(0)$ is determined by η_g given in Eq. 4. This has exactly the same form as Eq. 6 of Ref. 11, which finds (from a detailed analysis of a number of experiments) $\alpha^2 = 0.43$ for $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ and $\alpha^2 = 0.46$ for $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$. The conclusions here are however completely different from those drawn in Ref. 11 which, based on previous theoretical work, considered α^2 to be a Fermi liquid correction with a not unreasonable value. The conclusion of this article is that the experimentally determined value of α^2 implies a value of v_F^b significantly smaller than v_F , which is not physically reasonable. One of the essential features of strongly correlated electron systems such as the copper-oxide superconductors is that the strong electron-electron correlations are expected to produce narrow energy bands and large quasiparticle masses, leading to $v_F < v_F^b$.

The renormalization of the spin susceptibility due to Fermi-liquid interactions can be calculated in a similar way. The Zeeman interaction of the spin of an electron with the magnetic field contributes an Antisymmetric external field of A_g symmetry to the Hamiltonian. It follows that the magnetic moment per unit area of a copper oxide plane is

$$M = -\frac{\mu_B}{L^2} \sum_k [f(E_{k,1}) - f(E_{k,-1})] = \chi H \quad (16)$$

where

$$\chi(T) = \frac{\chi_0(T)}{1 + F_{A_g}^A(T)}, \quad \chi_0(T) = \frac{\mu_B^2 \ln 2 k_B T}{\pi\hbar^2 v_F v_2}. \quad (17)$$

Note that here also the low-temperature clean-limit linear in T magnetic susceptibility is not changed by Fermi-liquid interactions. These affect only terms of order T^2 and higher in the susceptibility.

This article has given a detailed description of both Fermi-liquid effects and band structure effects within the framework of a quasiparticle picture of the low-temperature properties of d -wave superconductors. This

opens the way for a detailed quantitative experimental test of the quasiparticle picture of the low-temperature properties. A classification of Fermi-liquid effects is given that separates the strong renormalization and weak renormalization effects according to a symmetry property. The application of the results to the interpretation of penetration depth measurements is of particular interest. This corresponds to the weak (and in fact negligible) Fermi-liquid renormalization case, and the ultimate conclusion is that the experimental results imply a band Fermi velocity which is smaller than the corresponding quasiparticle Fermi velocity, which is an unphysical result. Clearly there are at present problems with the quantitative aspects of the quasiparticle picture of the low-temperature properties of the high T_c superconductors and further study is desirable.

I acknowledge stimulating discussion with L. Taillefer, the hospitality of P. Nozières, and the Theory Group of the Institut Laue Langevin where much of this work was done, and the support of the Canadian Institute for Advanced Research and of the Natural Sciences and Engineering Research Council of Canada.

-
- ¹ W. N. Hardy et al., Phys. Rev. Lett. **70**, 3999 (1993).
 - ² M. Prohammer and J. P. Carbotte, Phys. Rev. **43**, 5370 (1991).
 - ³ J. A. Martindale et al., Phys. Rev. B **47**, 9155 (1993).
 - ⁴ P. A. Lee, Phys. Rev. Lett. **71**, 1887 (1993).
 - ⁵ M. J. Graf et al., Phys. Rev. B **53**, 15147 (1996).
 - ⁶ L. Taillefer et al., Phys. Rev. Lett. **79**, 483 (1997).
 - ⁷ K. A. Moler et al., Phys. Rev. B **55**, 3954 (1997).
 - ⁸ D. A. Wright et al., Phys. Rev. Lett. **82**, 1550 (1999).
 - ⁹ A. Hosseini et al., Phys. Rev. B **60**, 1349, (1999).
 - ¹⁰ M. B. Walker and M. F. Smith, Phys. Rev. B **61**, 11285, (2000).
 - ¹¹ M. Chiao et al., Phys. Rev. B (to appear); cond-mat/9910367.
 - ¹² A. Kaminski et al., Phys. Rev. Lett. **84**, 1788 (2000).
 - ¹³ T. Valla et al., Science **285**, 2110 (1999).
 - ¹⁴ E. W. Carlson et al., Phys. Rev. Lett. **83**, 612 (1999).
 - ¹⁵ A. J. Millis et al., J. Phys. Chem Solids **59**, 1742 (1998).
 - ¹⁶ A. C. Durst and P. A. Lee, cond-mat/9908182, Phys. Rev. B (in press).
 - ¹⁷ D. Pines and P. Nozières, *Theory of Quantum Liquids - Volume I*, Addison Wesley (1989).
 - ¹⁸ O. Betbeder-Matibet and P. Nozières, Ann. Phys. (NY) **51**, 392 (1969).
 - ¹⁹ A. I. Larkin and A. B. Migdal, Sov. Phys. JETP **17**, 1146 (1963).
 - ²⁰ A. J. Leggett, Phys. Rev. **140**, A1869 (1965).
 - ²¹ F. Gross et al., Z. Phys. B **64**, 175 (1986).
 - ²² D. Xu et al., Phys. rev. B **51**, 16233 (1995).